


In the Claims:

The text of all claims under examination is submitted, and the status of each is identified. This listing of claims replaces all prior versions, and listings, of claims in the application.

1. **(currently amended)** A process for the preparation of a water- and/or oil-based personal care composition characterized in that ~~which comprises incorporation into said composition a~~ cationic liquid dispersion copolymer ~~prepared by the emulsion polymerization of~~ an aqueous phase of the components

(a) a cationic monomer of formula (I),



wherein

R₁ is hydrogen or methyl,

R₂ is hydrogen or C₁-C₄alkyl,


R₃, R₄ and R₅ are independently from each other hydrogen or C₁-C₄alkyl,

n is a integer from 1 – 5, and

Y is a counterion,

and

(b) a monomer of formula (II)



wherein

R₆ signifies hydrogen or methyl,

R₇ signifies hydrogen or methyl, and

R₈ and R₉ signify independently from each other hydrogen or C₁-C₄alkyl,

with the proviso that at least one of the substituents R₆, R₈ and R₉ is

C₁-C₄alkyl,

and

(c) optionally at least one cross-linking agent, which contains at least two ethylenically unsaturated moieties is prepared;

an oil phase is prepared.

the aqueous and oil phase are mixed to form a water-in-oil emulsion,
the monomer components are polymerized to form a copolymer, and
cosmetically functional agents are added

~~wherein the monomers I and II are combined in an aqueous phase which is mixed with an oil phase and polymerized,~~

~~characterized in that the cationic liquid dispersion copolymer consists essentially of monomer (I) and monomer (II).~~

2. **(currently amended)** A process according to Claim 1 characterized in that the ~~cationic liquid dispersion~~ copolymer consists essentially of

20 – 95 wt-% of a monomer of formula (I) and of
5 – 50 wt-% of a monomer of formula (II).

3. **(currently amended)** A process according to Claim 1 characterized in that the ~~cationic liquid dispersion~~ copolymer consists essentially of

40 – 90 wt-% of a monomer of formula (I) and of
10 – 40 wt-% of a monomer of formula (II).

4. **(currently amended)** A process according to Claim 1 characterized in that the ~~cationic liquid dispersion~~ copolymer comprises 50 – 500 ppm of at least one cross-linking agent based on the total amount of the copolymer.

5. **(previously presented)** A process according to claim 1 characterized in that

R₁ is hydrogen or methyl,

R₂ is hydrogen or methyl,

R₃, R₄ and R₅ are independently from each other hydrogen or methyl,

n is an integer from 1 – 4, and

Y is Cl; Br; I; hydrogensulfate or methosulfate.

6. **(previously presented)** A process according to claim 1 characterized in that

R₆ signifies hydrogen or methyl,

R₇ signifies hydrogen or methyl, and


R₈ signifies hydrogen or methyl, and

R₉ signifies hydrogen or methyl,

with the proviso that at least one of the substituents R₆, R₈ and R₉ is methyl.

7. **(currently amended)** A process according to Claim 1, characterized in that the aqueous phase of components ~~-comprising the emulsion polymerization of~~

- (a) a cationic monomer of formula (I),




wherein

R₁, R₂, R₃, R₄ and R₅ are independently from each other hydrogen or methyl,

n is 1, 2 or 3, and

Y is a counterion, and

- (b) a monomer of formula (II)



wherein

R₆ signifies hydrogen or methyl, R₇ signifies hydrogen or methyl,

R₈ signifies hydrogen or methyl, and

R₉ signifies hydrogen or methyl,

with the proviso that at least one of the substituents R₆, R₈ and R₉ is methyl, and

- (c) optionally at least one cross-linking agent selected from the group consisting of tetra allyl ammonium chloride; allyl-acrylamides and allyl-methacrylamides; bisacrylamidoacetic acid and N,N'-methylene-bisacrylamide;

is prepared

~~characterized in that the cationic liquid dispersion copolymer consists essentially of monomer of formula I and monomer of formula~~

8. **(currently amended)** A process according to Claim 7 characterized in that the ~~cationic liquid dispersion~~ copolymer consists essentially of

20 – 95 wt-% of a cationic monomer of formula (I),

11. **(currently amended)** A ~~method~~process of preparing an oil/water emulsion-based personal care ~~the~~ composition according to claim 1 which composition comprises:

0.5 – 10 wt-% of the ~~cationic liquid dispersion~~ copolymer,
2 – 25 wt-% of at least one oil-component,
0 – 25 wt-% of at least one adjuvant and/or additive, and
water up to 100 wt-%.

12. **(currently amended)** A ~~method~~process ~~according to claim 1~~ of preparing an oil-based personal care ~~the~~ composition according to Claim 1, which composition comprises

0.5 – 10 wt-% of the ~~cationic liquid dispersion~~ copolymer,
50 – 99 wt-% of at least one oil-component, and
0 – 25 wt-% of at least one adjuvant and/or additive.

13. **(previously presented)** A process according to claim 5 characterized in that

R₁ is hydrogen,
R₂ is hydrogen,
R₃, R₄ and R₅ are methyl,
n is an integer from 1 – 4, and
Y is Cl; Br; I; hydrogensulfate or methosulfate.

14. **(previously presented)** A process according to claim 6 characterized in that

R₆ signifies hydrogen,
R₇ signifies hydrogen, and
R₈ signifies hydrogen or methyl, and
R₉ signifies hydrogen or methyl,
with the proviso that at least one of the substituents R₈ and R₉ is methyl.

15. **(currently amended)** A process according to claim 8 characterized in that the ~~cationic liquid dispersion~~ copolymer consists essentially of

40 – 90 wt-% of a cationic monomer of formula (I),
and
10 – 40 wt-% of a monomer of formula (II)

and

100 – 300 ppm (based on the total amount of monomers) of at least one compound selected from the group consisting of tetra allyl ammonium chloride and N,N'-methylene-bisacrylamide.